

## **Product Specification**

| Item #           | SCGIN200300BLK                             |  |  |
|------------------|--|--|--|
| Description      | VACUUM POUCH 200 X 300 GINGHAM BLACK/WHITE |  |  |
| Unit             | 1000                                       |  |  |
| Pallet Qty       | 75   |  |  |
| Product Category | 41215 Gingham Pouches                      |  |  |
| Unit Weight      | 7  |  |  |
|                  |  |  |  |

## **Specification Details**

PA/PE Multilayer Co-extruded barrier Blown film.

Excellent Sealability, Mechanical strength, barrier property.

| SR No | Property   | ASTM   | MIC   |
|-------|--|--------|-------|
| 1     | AVG. THICKNESS<br>2σ (±10%)                      |        | 65    |
| 2     | DART IMPACT (gm<br>at 66cm                       |        | > 600 |
| 3     | TENSIL (N/15mm)                                  |        |       |
|       | MD   | D-882  | > 30  |
|       | TD   | D-882  | > 30  |
| 4     | ELONGATION (%)                                   |        |       |
|       | MD   | D-882  | > 400 |
|       | TD   | D-882  | > 400 |
| 5     | C.O.F. (F□F)<br>static-dynamic                   |        |       |
|       | INNER  | D-1984 | < 0.3 |
| 6     | SEAL STRENGTH<br>(N/15mm)                        |        | > 20  |
| 7     | OTR 23°C/0 % Rh<br>(CC/m <sup>2</sup> /day)      | D-3985 | ≤ 60  |
| 8     | WVTR 38° C &<br>90%RH(gm/m <sup>2</sup><br>/day) | F-1249 | ≤ 6   |

Storage & material handling Condition recommendation:

Packed or unpacked products cannot be stored outside protect from rain and direct sun light. Product should be stored in a clean, cool, dry place at room temperature not exceeding 40°C. The Products must be stored properly and avoid direct contact to floor, walls, away from boilers, heaters, radiators, chemicals, water etc. Please remove all the packaging material before using the products. This film is suitable for 6 months from the date of the production.

The films are made of raw materials (inputs) such as polymers used in the above products suitable for food contact in according to FDA and/or EC relevant regulations. All information given on this datasheet is approximated value, correct to our best knowledge and relates to unformed film only. Typical values not specified limits. We assume no liability for any loss or damaged for use of this data sheet.

We further confirm that the manufacture of this product complies with EU Directive 2023/2006.

## **Customer Approval of Specification**

Please sign and return this specification to **technical@scobie-junor.co.uk** to confirm formal acceptance of this specification. All specifications issued will be deemed to be accepted if no communication to the contrary is received after 10 working days.

| Print Name |  |
|------------|--|
| Position   |  |
| Date       |  |

While we have taken all reasonable steps to verify the accuracy of the information contained in this specification, no warranties are given to this effect and purchasers should determine for themselves whether products are suitable for their own specific use. The information contained in this specification is intended for the customer it has been issued to. It must not be reproduced, or the information contained therein passed on to any third party without the written consent of Scobie & Junor.

## **Issued electronically by Scobie & Junor (Estd. 1919) Ltd** Certified accurate on 28/04/2024



© 2024 Scobie & Junor (Estd. 1919) Ltd Group Headquarters 1 Singer Road, East Kilbride, Scotland, G75 0XS Tel: 01355 237041 Fax: 01355 576343 www.scobiesdirect.com Registered Scotland # 10710 VAT # GB 659 1432 23

Naas Branch Unit A3, M7 Business Park Naas, Co Kildare, Ireland Tel: 045 856 747 Fax: 045 856 726 Freephone: 1800 30 1919 VAT # IE 6540968 P