



### 652061200

# **COATED FSC -P100- YG D**

Face	One side coated paper	FSC Mix Credit, is	designed for high-end	. pressure sensitive label applications	S.
Face	One side coated paper	. FSC MIX Credit. IS	designed for high-end.	. Dressure sensitive lab	ei addiication:

This grade features excellent opacity and high brightness combined with a semi-gloss finish for

excellent printability.

Adhesive Acrylic based, permanent adhesive for general use. Suitable for numerous applications on clean, dry

and flat surfaces,including slightly rough and curved substrates. It's not suitable for wet applications.

Excellent performance during slitting, high speed matrix-stripping and automatic labelling.

Liner Yellow, FSC Mix Credit, supercalandered siliconised glassine paper. Specially designed for high speed

conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

Face	Method	Unit	Target			
Basis Weight	ISO 536	g/m²	78 ± 4			
Thickness	ISO 534	μm	67 ± 4			
Adhesive						
Peel adhesion 90°	FTM 2 st.st	N/m	min.240	(min. 6 N/25mm)		
Loop Tack	FTM 9 glass	N/m	min.480	(min. 12 N/25mm)		
Min. appl temperature		°C	0			
Service temperature		°C	-20 / +80			
Liner						
Basis Weight	ISO 536	g/m²	56 ± 2			
Thickness	ISO 534	μm	50 ± 3			
Transparency	DIN 53147	%	49			
Laminate						
Thickness	ISO 534	μm	125 ± 5			

## **Application and use**

This product is designed for wide range of promotional and industrial labelling applications where a good semi gloss appearance is required.

#### **Conversion and Printing**

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

## **Packaging**

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

#### **Shelf Life and Storage Conditions**

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22  $^{\circ}$ C  $\pm$  2  $^{\circ}$ C with a relative humidity of 50 %,  $\pm$  5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.